

Swab/Solvent Compatibility Chart

Solvent	Head Substrate	
	Foam	Polyester
Acetic Acid	U	U
Acetone	S	U
Acetonitrile	U	U
Ammonia, Anhydrous	U	U
Aniline	S	U
Benzene	S	U
Carbon Tetrachloride	S	U
Chloroform	S	U
Chlorophenol	D	D
Chromic Acid	D	D
Cyclohexane	S	U
Dimethylformamide	D	S
Dimethylsulfoxide	D	S
Ethyl Acetate	S	U
Ethyl Alcohol	U	U
Ethyl Chloride	S	U
Formic Acid	D	U
Hexane	U	U
Hydrochloric Acid 48%	D	D
Hydrogen Peroxide	D	U
Isopropyl Alcohol	U	U
Methanol	S	U
Methyl Ethyl Ketone	S	U
Methylene Chloride	S	U
Nitric Acid 100%	D	D
Nitrobenzene	S	U
Perchloroethylene	U	U
Phosphoric Acid 85%	D	U
Sodium Hydroxide 36%	S	U
Sulfuric Acid 98%	D	D
Toluene	S	U
Trichloroethylene	S	U
Vinyl Acetate	S	U
Water	U	U
Xylene	S	U

U– Unaffected

S– Swells

D– Degrades

Compatibility is determined at room temperature.